

DURAFLEX™ 190TG SBS

Technical Data Sheet

Product Name: DuraFlex™ 190TG SBS

Classification: SBS Modified Bitumen Roof Membrane

Product Description: DuraFlex™ 190 SBS is a granule surfaced, premium SBS (Styrene-Butadiene-Styrene) torch applied membrane. Manufactured with a non-woven polyester mat and a fiberglass strand for enhanced dimensional stability, high tear strength and puncture resistance. DuraFlex™ 190 SBS is saturated and coated with a premium quality, asphaltic bitumen and SBS elastomers for a highly durable, flexible and easily maintainable membrane. It is designed for use as a cap sheet and for flashing membrane in modified bitumen torch applied SBS roof systems.

Application Method: DuraFlex™ 190TG SBS is applied using compatible hot asphalt or SBS cold adhesive.

Approvals: Meets ASTM D 6164 Type I, Grade G. U.S. Ply products are listed or approved with Underwriter's Laboratories (UL) and Factory Mutual (FM). Contact U.S. Ply, Inc. for specific/applicable codes.

Product Data: DuraFlex™ 190TG SBS (typical)

Thickness: 4.0 mm (157 mils)

Weight: 105 lbs/roll (48 kg/m²)

Roll Dimensions: 39 3/8" x 32' 9" (1m x 10m). Each roll is approximately 107.6 sq. ft.

Physical Properties (ASTM D 5147):	Test Results	ASTM D 6164 Minimum
Tensile Strength (lbf/in), 0°F, (MD/XMD)	118/97	70 lbf/in
Tensile Strength (lbf/in), 73°F, (MD/XMD)	105/78	50 lbf/in
Elongation (% @ Max Load), 0°F, (MD/XMD)	30/26	20%
Elongation (% @ Max Load), 73°F, (MD/XMD)	55/57	35%
Elongation (% @ 5%, Max Load), 73°F, (MD/XMD)	57/68	38%
Tear Strength (lbf), (MD/XMD), 73°F, minimum	116/92	55 lbf
Low Temperature Flexibility, (°F), maximum	0°F (-18°C)	0°F
Dimensional Stability, %, maximum	< 0.2%	1%
High Temperature Stability, (°F)	215°F (101°C)	215°F
Granule Embedment, g/m ² , avg loss	<1.2 g	< 2 g

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative.

U.S. PLY, INC.

A DANNY ADAIR COMPANY

Corporate Headquarters: P.O. Box 11740, Fort Worth, Texas 76110

TOLL-FREE: 866-PUSH-PLY (866) 787-4759 • Local: (817) 413-0103 • Fax: (817) 413-8221

Website: www.usply.com • Email: sales@usply.com

April 2007