

Product Data Sheet

DURAFLEX® 190FR SBS

Physical Properties (ASTM D5147):	Test Results	ASTM D6164 Minimum Standard
Tensile Strength (lbf/in), 0°F (MD/XMD)	118/97 lbf/in	70 lbf/in
Tensile Strength (lbf/in), 73°F (MD/XMD)	105/78 lbf/in	50 lbf/in
Elongation (% @ Max Load), 0°F, (MD/XMD)	30/26%	20%
Elongation (% @ Max Load), 73°F (MD/XMD)	55/57%	35%
Elongation (% @ 5% Max Load), 73°F (MD/XMD)	57/68%	38%
Tear Strength (lbf), (MD/XMD), 73°F, minimum	116/92 lbf	55 lbf
Low Temperature Flexibility, (°F), maximum	0°F (-18°C)	0°F
Dimensional Stability, %, maximum	<0.2%	1%
High Temperature Stability, (°F)	250°F (121°C)	215°F
Granule Embedment, g/m ² avg. loss	1.3	<2 g

DuraFlex® 190FR SBS is a fire-resistant, granule surfaced, premium SBS (Styrene-Butadiene-Styrene) mop or cold adhesive applied membrane. Manufactured with a non-woven polyester mat and fiberglass strands for enhanced dimensional stability, high tear strength and puncture resistance. It is saturated and coated with high quality, asphaltic bitumen and SBS elastomers for a durable, flexible and easily maintainable membrane. Designed for use as a cap sheet in modified bitumen roof systems.

Product Name: DuraFlex® 190FR SBS

Classification: SBS Modified Bitumen Base Sheet

Application Method: DuraFlex® 190FR SBS is applied using hot asphalt or SBS cold adhesive.

Approvals: Meets ASTM D 6164 Type I, Grade G. DuraFlex® 190FR SBS is UL Classified with Underwriter's Laboratories (UL), is Factory Mutual (FM) Approved, and listed with Florida Building Code (FBC) FL-8077, and Texas Department of Insurance (TDI) RC-123. Contact U.S. Ply, Inc. for specific/applicable codes.

Product Data: DuraFlex® 190FR SBS (typical)

Thickness: 4.4 mm (173 mils)

Weight: 105 lbs/roll (48 kg/m²)

Roll Dimensions: 39 3/8" x 32' 9" (1m x 10m). Each roll is approximately 1 square.

Green Standards Information: DuraFlex® 190FR SBS contains approximately 8.8% of recycled materials by product weight. 2.4% of materials are comprised of post consumer recycled materials and 6.4% of materials are comprised of pre consumer recycled materials. The post consumer recycled materials are derived from recycled post consumer plastics which averts disposal in landfills or commercial dumps. The pre consumer recycled materials are derived from reclaimed non-hazardous coal combustion by-product waste which averts disposal of coal by-product waste in landfills or commercial dumps.

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product

purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY U.S. PLY, INC. EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



CORPORATE HEADQUARTERS: P.O. BOX 11740, FORT WORTH, TEXAS 76110

TOLL-FREE: 866-PUSH-PLY (866) 787-4759 LOCAL: (817) 413-0103 • FAX: (817) 413-8221
WWW.USPLY.COM